

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D04B 1/14	A1	(11) International Publication Number: WO 96/27039 (43) International Publication Date: 6 September 1996 (06.09.96)
(21) International Application Number: PCT/BE96/00019 (22) International Filing Date: 23 February 1996 (23.02.96) (30) Priority Data: 9500414 2 March 1995 (02.03.95) NL (71) Applicant (for all designated States except US): N.V. SYNCO-GLAS S.A. [BE/BE]; Drukkerijstraat 9, B-9240 Zele (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): CLAEYS, Etienne [BE/BE]; Oude Heerwegheide 63a, B-9250 Waasmunster (BE). (74) Agent: VAN SOMEREN, Petronella, Francisca, Hendrika, Maria; Arnold & Siedsma, Sweelinckplein 1, NL-2517 The Hague (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>In English translation (filed in Dutch).</i>
(54) Title: REINFORCEMENT MATERIAL (57) Abstract The invention relates to a strengthening material, for instance for use as textile reinforcement in composites, comprising at least one thickness-providing layer formed by a non-woven or a knit of glass fibre and at least one strengthening layer connected thereto on at least one side thereof, wherein at least one of both strengthening layers is preferably embodied in glass fibre. Further described is a composite provided with a strengthening material according to the invention.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

REINFORCEMENT MATERIAL

The present invention relates to a strengthening material for instance for use as textile reinforcement in composites.

Currently placed into composites consisting of
5 plastic strengthened with a textile reinforcement are woven fabrics, mats, membranes, non-wovens etc.

In addition, a number of layers of textile reinforcement are also often employed simultaneously to obtain the required stiffness and resistance. The different
10 layers are then mutually connected to thus obtain the desired thickness of the reinforcement. Mutual connection of these multi-layer structures can be carried out for instance by means of knitting machines (the so-called Rachel machines) which mutually connect the different
15 layers by means of a fine yarn, using for instance the chain stitch. The drawback of employing for instance a polyester strengthening thread is that this does not withstand particularly well the effect of moisture and corrosive substances. In addition, the materials used are
20 often not compatible with the resin, whereby they do not adhere thereto. This does not enhance the durability of the final product.

Composites provided with a textile reinforcement are applied for instance in flat objects such as panels,
25 although more complicated pieces, such as boats, bumpers, junction boxes, bathtubs, telephone poles, tubes, profiles etc. are nowadays also often made of composite materials.

In the manufacture of flat composites such as for
30 instance panels, most known strengthening woven fabrics and mats are sufficiently satisfactory. However, when complex shapes are made the textile reinforcements known up to the present time do not allow of sufficient moulding and folding or they behave in uncontrolled manner.
35 Woven fabrics in particular are difficult to deform. Non-

wovens quite often tend to behave uncontrolledly and/or tear.

The multi-layer structures also deform little or not at all when stretched if at least one of the layers is
5 formed by a woven fabric. If one of the layers consists of a non-woven they deform in an uncontrolled manner.

It is the object of the invention to obviate the above mentioned drawbacks of particularly the multi-layer textile reinforcement. The invention has for its further
10 object to provide a multi-layer textile reinforcement wherein composites of a great thickness (1 to 10 mm) can be made. Finally, the invention also has for its object to increase the durability of the composites provided with a textile reinforcement.

15 This is achieved by the invention with a strengthening material comprising at least one thickness-providing layer formed by a non-woven or a knit of glass fibre and at least one strengthening layer connected thereto on at least one side thereof. At least one of the strengthening
20 layers is herein preferably embodied in glass fibre.

The use of a knit or a non-woven of glass fibre as central layer in such strengthening materials has not been described before.

With the strengthening material according to the
25 invention stretching and draping of the reinforcement can take place in a regular and reproducible manner. Composites manufactured using the strengthening material according to the invention possess locations of different thicknesses which are predictable and reproducible.

30 In a particularly advantageous embodiment of the invention at least the middle layer is formed by a knit of glass fibre. Such a knit has an excellent deformability. The weight, thickness and deformability of the strengthening material can vary in accordance with the
35 application.

In another preferred embodiment the middle layer is a non-woven embodied in glass fibre.

The strengthening material can be used in the manufacture of plastic composites by means of injection,
40 vacuum technique, RIM, RTM etc.

With the strengthening materials according to the invention it becomes possible to realize a perfect resin transport over the full surface and through the full thickness of the workpiece. In addition, a regular and controlled deformation of the strengthening layers connected to the knit or the glass fibre non-woven becomes possible during moulding of the workpiece. The occurrence of tears and irregularities is hereby prevented, even at a local stretching of 100%. The middle layer, which is preferably formed by a knit or a non-woven in glass fibre, provides thickness to the strengthening material whereby the desired stiffness of the composites can be obtained.

It has been found that the delamination resistance of the composite is already significantly higher when at least the middle layer is embodied in glass fibre. Preferably however, the strengthening material is wholly embodied in glass fibre.

The strengthening layers can vary in weight, thickness and structure. They can be arranged on one or both sides of the middle layer. One or more of such layers can be used on each side. As strengthening layers can be used non-wovens, membranes, mats, woven fabrics, webs and the like. It will be apparent to the skilled person that, subject to the application, any desired per se known strengthening layer can be used as long as they are applied in combination with either a knit or a non-woven of glass fibre.

The connection of the layers is effected by means of per se known techniques, such as knitting, sewing, needle punching or adhesion. Combinations of different techniques can optionally be used. Needle punching or chemical binding (adhesion) is however recommended.

In the case of needle punching the different layers are fixed together in that the threads of the strengthening material are punched through by needles. Parts of the threads are herein pushed through the other layers, thereby resulting in a mechanical connection. Needle punched material has a number of advantageous properties. The strengthening material thus becomes more voluminous

4.

and woolly as a whole, whereby the surface is smoother and finer. This also has the result that composites can be made with a lower glass content. This is particularly advantageous with a view to cost. A three-dimensional strengthening results from a plurality of threads, or parts thereof, being pushed through the full thickness of the strengthening material. The delamination resistance of such a material is therefore very great. When only layers of glass are used and these are fastened to each other by needle punching, the strengthening material consists entirely of glass. Composites made herewith have a better resistance to the action of moisture and corrosive substances than composites wherein the different layers of the strengthening material are fastened together by means of for instance a polyester thread. Moreover, the strengthening material manufactured by needle punching is likewise suitable for use in composites wherein fire resistance is important (for instance phenol resins).

Chemical binding of the layers takes place by spraying or sprinkling the layers with a fine powder of a thermoplastic or thermosetting plastic. The whole is thereafter heated and pressed together, whereby the powder melts and the different layers adhere to each other. The advantage of such a manner of connection is that the thermoplastic powder dissolves in the resin used to form the composite and participates fully in the polymerization. The skilled person will appreciate that the choice of powder and resin must be such as to enable dissolving and participation in the polymerization. The advantage of chemical adhesion is again that the synthetic connecting thread in the composite is absent.

The strengthening material according to the invention makes it possible to perform the moulding of the end product, in flat or complex shapes, in a one-step process.

The invention further relates to composites provided with a strengthening material according to the invention.

The present invention will be further elucidated with reference to the accompanying example, which is only

given by way of illustration and is not intended to limit the invention in any way whatsoever.

EXAMPLES

5 EXAMPLE 1

A strengthening material according to the invention is manufactured on a conventional needle punching machine. The material consists of a middle layer formed by a knit embodied in glass fibre. The glass fibre is
10 chosen such that it is suitable for processing with the used resin types. The knit has a weight of 200 g/m² and a thickness of 1.5 mm.

For strengthening purposes a non-woven is arranged on both sides of this middle layer. In this specific case
15 a glass mat is used which is made in conventional manner and consists of chopped strands mutually adhered with adhesive powder. The fibres have a thickness of 10-50 tex and a length of 50 mm. The weight of the mat is 600 g/m². Such a mat is also referred to as CSM (= Chopped Strand
20 Mat).

The three layers are mutually connected by means of the needle punching technique.

Starting from this textile reinforcement a composite is manufactured in complex shape by means of pressing,
25 injecting and vacuum technique. The thickness of the composites formed in this manner is varied.

It has been found that in all the manufactured composites the stretching of the strengthening material in the complex shape of the matrix proceeds in the same
30 manner as the manner in which the knit itself can be draped. The fibres of the glass mats connected to the knit by means of the needle punching technique follow the deformation of the knit whereby a regular, controlled and reproducible stretching of the glass mats is ensured. The
35 result is that the end product does not have locations with resin concentrations alternating with locations of glass fibre concentrations. Either type of concentration would cause weak spots in the composite. Due to the great draping capacity of the middle layer, in this example the
40 knit, it is possible to realize composites which locally

require very large deformations of more than 100% of the strengthening material.

EXAMPLE 2

5 The same process as in example 1 is applied but instead of a knit a non-woven in endless glass fibre is used as middle layer between the two strengthening layers.

10 In this manner a strengthening material is obtained with which a 100% glass fibre-reinforced composite can be realized. This composite has a much higher delamination resistance than a composite with synthetic membrane as middle layer.

CLAIMS

1. Strengthening material, for instance for use as textile reinforcement in composites, comprising at least one thickness-providing layer formed by a non-woven or a knit of glass fibre and at least one strengthening layer
5 connected thereto on at least one side thereof.
2. Strengthening material as claimed in claim 1, characterized in that at least one of the strengthening layers is embodied in glass fibre.
3. Strengthening material as claimed in claim 2,
10 characterized in that all layers are embodied in glass fibre.
4. Strengthening material as claimed in any of the claims 1-3, characterized in that the different layers are mutually connected by means of knitting techniques
15 and/or adhesion and/or needle punching and/or sewing.
5. Strengthening material as claimed in any of the claims 1-4, characterized in that the strengthening layer is a non-woven, a woven fabric, a mat, a web or a membrane.
- 20 6. Strengthening material as claimed in any of the claims 1-5 wholly or partially impregnated with resin.
7. Composite provided with a strengthening material as claimed in any of the foregoing claims.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/BE 96/00019

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D04B1/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 D04B D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR,A,2 628 448 (ETS LES FILS D'AUGUSTE CHOMARAT & CIE) 15 September 1989 see page 4, line 12 - line 30; figure 1 ---	1,2,5,7
X	US,A,4 911 973 (DUNBAR) 27 March 1990 see column 3, line 19 - line 59 ---	1-7
A	FR,A,2 568 275 (ETS LES FILS D'AUGUSTE CHOMARAT & CIE) 31 January 1986 ---	
A	DE,A,42 18 860 (FORSCHUNGSINSTITUT FÜR TEXTILTECHNOLOGIE CHEMNITZ) 16 December 1993 ---	
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* "&" document member of the same patent family

Date of the actual completion of the international search

11 June 1996

Date of mailing of the international search report

21. 06. 96¹

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Van Gelder, P

INTERNATIONAL SEARCH REPORT

International Application No
PCT/BE 96/00019

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>AUTOMOTIVE ENGINEERING, vol. 102, no. 8, August 1994, WARRENDALE, PA, US, pages 21-24, XP000464639 "Knitted-fiber-reinforced composites" -----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/BE 96/00019

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2628448	15-09-89	CA-A- 1310178 EP-A,B 0333602	17-11-92 20-09-89
US-A-4911973	27-03-90	NONE	
FR-A-2568275	31-01-86	BE-A- 902842 DE-U- 8521108	04-11-85 09-01-86
DE-A-4218860	16-12-93	NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.